


# POT & CUT CORES

**Meisongbei**

Material: M3



Type	Fig	Dimension(mm)						
		A	B	C	D	E	F	G
POT9 × 5	1	9.20±0.20	7.70±0.20	3.75±0.15	2.10±0.10	2.65±0.10	1.90±0.10	
POT11 × 7	1	11.10±0.20	9.20±0.20	4.60±0.10	2.10±0.10	3.25±0.10	2.30±0.10	
POT14 × 8	1	14.00±0.25	11.60min	6.00max	3.10±0.10	4.20±0.20	2.80min	
POT18 × 11	1	18.10±0.50	15.20±0.40	7.45±0.25	3.05±0.15	5.65±0.15	3.80±0.20	
POT22 × 14	1	21.70±0.50	18.30±0.50	9.15±0.25	4.50±0.20	6.85±0.15	4.80±0.20	
POT26 × 16	1	25.50±0.50	21.60±0.40	11.30±0.20	5.70±0.20	8.10±0.10	5.90±0.20	
POT30 × 20	1	30.10±0.60	25.50±0.60	13.25±0.35	5.50±0.20	9.85±0.15	7.25±0.25	
POT36 × 22	1	33.70±0.60	26.50min	13.50±0.30	23.70±0.50	12.05±0.20	9.25±0.20	
POT23 × 11	2	22.90±0.5	18.20±0.25	9.70±0.20	5.08±0.10	5.54±0.125	3.78±0.15	
CUT14 × 8	3	14.00±0.25	11.60min	6.00max	3.10±0.10	4.20±0.20	2.80min	9.40(+0.35/-0.15)
CUT18 × 11	3	18.10±0.50	15.20±0.40	7.45±0.25	3.05±0.15	5.65±0.15	3.80±0.20	11.90±0.20
CUT23 × 11	3	22.90±0.45	18.20±0.25	9.70±0.20	5.08±0.10	5.54±0.125	3.78±0.15	15.20±0.25
CUT30 × 19	3	30.40±0.60	25.40±0.60	13.30±0.35	20.30±0.40	9.50±0.20	6.70±0.30	17.50min
CUT33 × 19	3	33.70±0.60	26.50min	13.50±0.30	23.70±0.50	9.50±0.20	6.60±0.20	
CUT33 × 24	3	35.75±0.75	30.55±0.75	15.80±0.40	5.50±0.20	11.25±0.15	7.60±0.30	

Type	Effective Parameter				AL(nH/N <sup>2</sup> )	Weight(g)
	C1 (mm <sup>-1</sup> )	Le (mm)	Ae (mm <sup>2</sup> )	Ve (mm <sup>3</sup> )	M3 (±25%)	
POT9 × 5	1.25	12.2	9.8	119.6	1200	0.9
POT11 × 7	0.96	15.5	16.2	251.1	1550	1.8
POT14 × 8	0.789	19.8	25	495	2130	3.2
POT18 × 11	0.579	25.8	43.3	1120	2960	6.6
POT22 × 14	0.502	31.6	63	2000	3300	13
POT26 × 16	0.4	37	93.9	3531	4600	21
POT30 × 20	0.331	45	136	6100	5800	35
POT36 × 22						
POT23 × 11	0.497	31.5	63.4	1197		13.4
CUT14 × 8	0.906	21.1	23.3	492	1930	2.7
CUT18 × 11	0.67	27.2	40.6	1110	2500	5.4
CUT23 × 11	0.497	28.6	61	1746	4150	10
CUT30 × 19	0.422	46.4	110	5104	4500	24.5
CUT33 × 19						
CUT33 × 24	0.257	52	202	10600	9000	62

SHANGHAI MEISONGBEI ELECTRONICS CO.,LTD

NO.528 Kangding Road,Jing'An,Shanghai Tel:0086-21-62883517 Fax:0086-21-62883519 www.meisongbei.com